

Cetol® Log Décor

A protective translucent satin finish that provides color and finish in one product for interior wood surfaces. The waterborne finish accentuates the natural grain and texture of all types of wood.

Translucent finish ensures maximum visibility of the wood grain

Unique satin coating seals and protects

Scratch resistant.

Quick drying

Low order

Excellent flow

Easy to clean

Urethane fortified

Waterborne

V.O.C. compliant

Cetol Log Décor is recommended for interior wood such as doors, paneling, logs, windows, furniture, etc. It is inappropriate for use on substrates such as tabletops, kitchen countertops and floors. Refer to the Sikkens Product Application Guide for details.

Method - Good quality long-haired, nylon polyester brush or synthetic pad applicator or spray.

Temperature - 50°F - 80°F (10°C - 27°C).

Cleaning of Equipment - Clean promptly with mild soap and clean water.

Coverage - Approximately 400-500 sq. ft. per U.S. gallon (10-12 sq. m. per liter), per coat on smooth wood.

Drying Time - Touch dry after 1-2 hours; recoatable after 4 hours.

CHARACTERISTICS

USE

APPLICATION

Viscosity - 3.3 - 3.9 Poise at 73°F (23°C)
Density - 1.02 - 1.06 kg/dm³
Solids by Weight - 27.0 - 29.0%
Solids by Volume - 24.5 - 25.5%
Gloss Level - Satin Finish
Flow - Very Good
Adhesion - Good
V.O.C. - 2.47 pounds/gallon (296 grams/liter)

(006) Light Oak
(030) Opal White
(043) Caramel
(078) Natural
(996) Natural Light

U.S. gallon

Shelf Life - Approximately 2 years in an unopened container.

Storage - Protect from frost. Keep from freezing.

FLASHPOINT:

Cetol Log Décor > 212°F (100°C)

WARNINGS:

Do not take internally.
Keep out of reach of children.
Close container after use.

FIRST AID TREATMENT:

Refer to the Material Safety Data Sheet.

The technical information and suggestions for use made herein are based on Akzo Nobel Coatings Inc.'s research and experience and are believed to be reliable, but such information and suggestions do not constitute a warranty.

Since Akzo Nobel Coatings Inc. has no control over the conditions under which the product is transported, stored, handled, used or applied, buyers must determine for themselves by preliminary tests or otherwise, the suitability of the product for their purposes. When testing, the complete system that has been chosen must be applied.

PROPERTIES

COLOR RANGE

PACKAGING

STORAGE

HEALTH & SAFETY DATA

PRODUCT DISCLAIMER